

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : Paxwood Pty Ltd T/A Clever Choice Design Floors
Unit 1
164 Adderlely Street
West Auburn NSW 2144

Test Number : 22-000566
Issue Date : 7/04/2022
Print Date : 27/05/2022

Sample Description Clients Ref : "Classic Laminate Flooring"
Laminate flooring planks
Colour : Timber look
End Use : Flooring
Nominal Thickness : Approx 12mm



268960

56827

Page 1 of 2

© Australian Wool testing Authority Ltd
Copyright - All Rights Reserved

Samples, and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. The above test results are designed to provide THE CLIENT WITH GUIDANCE INFORMATION ONLY.

This document shall not be reproduced except in full and shall be rendered void if amended or altered.

This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved in advance by the Managing Director of AWTA Ltd.



Fiona McDonald
APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : Paxwood Pty Ltd T/A Clever Choice Design Floors
Unit 1
164 Adderlely Street
West Auburn NSW 2144

Test Number : 22-000566
Issue Date : 7/04/2022
Print Date : 27/05/2022

ASTM D5116-2017

Standard Guide for Small Scale Environmental Chamber Determination of Organism Emission from Indoor Materials/Products

Date of Testing 04/04/2022

Seal and Test Underside of the test specimen is placed on an inert glass plate to determine exclusively the emission of the upper surface, sealing the edge with aluminium foil in 10mm width

Test Specimen Size 300x200, 4 pieces mm
Test Time 24 Hrs
Test Temperature 23 degC
Test Humidity 50%
Loading Factor 0.24m2m3
Air Exchange 1 / h

	Cas No	Test Result Concentration (24 Hour) mg/m3	Emission Factor Test Result (24 Hour) mg/m2.h
Formaldehyde	50-00-0	0.015	0.063

Report JA22109A Tested at AWTA JSIC JinAo Testing Co. Ltd

268960

56827

Page 2 of 2

© Australian Wool testing Authority Ltd
Copyright - All Rights Reserved

Samples, and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. The above test results are designed to provide THE CLIENT WITH GUIDANCE INFORMATION ONLY.

This document shall not be reproduced except in full and shall be rendered void if amended or altered.

This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved in advance by the Managing Director of AWTA Ltd.



Fiona McDonald
APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR