

# AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing  
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031  
P.O Box 240, North Melbourne, Victoria 3051  
Phone (03) 9371 2400

## TEST REPORT

**Client :** Paxwood Pty Ltd T/A Clever Choice Design Floors  
Unit 1  
164 Adderlely Street  
West Auburn NSW 2144

**Test Number :** 22-000570  
**Issue Date :** 11/04/2022  
**Print Date :** 27/05/2022

**Sample Description** Clients Ref : "Vinyl Flooring"  
Vinyl flooring planks  
Colour : Timber look  
End Use : Flooring  
Nominal Thickness : Approx: 2.5mm



268976

56831

Page 1 of 3

© Australian Wool testing Authority Ltd  
Copyright - All Rights Reserved


Samples, and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. The above test results are designed to provide THE CLIENT WITH GUIDANCE INFORMATION ONLY.

This document shall not be reproduced except in full and shall be rendered void if amended or altered.

This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved in advance by the Managing Director of AWTA Ltd.



Fiona McDonald  
APPROVED SIGNATORY



MICHAEL A. JACKSON B.Sc.(Hons)  
MANAGING DIRECTOR

# AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing  
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031  
P.O Box 240, North Melbourne, Victoria 3051  
Phone (03) 9371 2400

## TEST REPORT

**Client :** Paxwood Pty Ltd T/A Clever Choice Design Floors  
Unit 1  
164 Adderlely Street  
West Auburn NSW 2144

**Test Number :** 22-000570  
**Issue Date :** 11/04/2022  
**Print Date :** 27/05/2022

### ASTM D5116-2017

#### Standard Guide for Small Scale Environmental Chamber Determination of Organism Emission from Indoor Materials/Products

**Seal and Test** Underside of the test specimen is placed on an inert glass plate to determine exclusively the emission of the upper surface, sealing the edge with aluminium foil in 10mm width

Test Specimen Size 380x240, 4 pieces mm  
Test Time 24 Hrs  
Test Temperature 23 degC  
Test Humidity 50%  
Loading Factor 0.36m2m3  
Air Exchange 1 / h

	Cas No	Test Result Concentration	Emission Factor Test Result
		(24 Hour)	(24 Hour)
		mg/m3	mg/m2.h
Formaldehyde	50-00-0	Not Detected	Not Detected

Date of Testing 08/04/2022

268976

56831

Page 2 of 3

© Australian Wool testing Authority Ltd  
Copyright - All Rights Reserved

Samples, and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. The above test results are designed to provide THE CLIENT WITH GUIDANCE INFORMATION ONLY.

This document shall not be reproduced except in full and shall be rendered void if amended or altered.

This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved in advance by the Managing Director of AWTA Ltd.



Fiona McDonald  
APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)  
MANAGING DIRECTOR

# AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing  
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031  
P.O Box 240, North Melbourne, Victoria 3051  
Phone (03) 9371 2400

## TEST REPORT

**Client :** Paxwood Pty Ltd T/A Clever Choice Design Floors  
Unit 1  
164 Adderlely Street  
West Auburn NSW 2144

**Test Number :** 22-000570  
**Issue Date :** 11/04/2022  
**Print Date :** 27/05/2022

### Remarks:

1. Formaldehyd and acetaldehyde were detected using HPLC method with ultraviolet detector, whereas other VOC's substances were detected by Gas chromatography/Mass spectrometry method.
2. In this Gas chromatography/Mass spectrometry method, the scan mode of SIM was employed for caprolactum detection, and TIC for others.

Tested by AWTA-JSIC JinAo Testing Co Limited - China.

Report Number: JA221098

268976

56831

Page 3 of 3

© Australian Wool testing Authority Ltd  
Copyright - All Rights Reserved

Samples, and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. The above test results are designed to provide THE CLIENT WITH GUIDANCE INFORMATION ONLY.

This document shall not be reproduced except in full and shall be rendered void if amended or altered.

This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved in advance by the Managing Director of AWTA Ltd.



Fiona McDonald  
APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)  
MANAGING DIRECTOR